



SOFT LEAD 1

Kelorex Energy

Elements	Amount	1110	1112	1113	1114	1115	1116	1118	1119	1120	1121
Pb	%Min	99.9793	99.9792	99.9769	99.988	99.9865	99.9882	99.9843	99.9707	99.9746	99.9861
Sn	%Max	<0.00005	<0.00005	0.00009	<0.00005	<0.00005	<0.00005	<0.00005	0.00049	0.00030	<0.00005
Ag	%Max	0.0019	0.0021	0.0025	0.0017	0.0018	0.0018	0.0020	0.0029	0.0023	0.0019
Sb	%Max	0.00022	0.00048	0.00054	0.00033	0.00028	0.00068	0.00091	0.00072	0.00057	0.00028
Bi	%Max	0.0146	0.0158	0.0163	0.0081	0.0102	0.0078	0.0097	0.0197	0.0178	0.0089
Cd	%Max	0.00003	0.00003	0.00003	0.00003	0.00003	0.00003	0.00003	0.00004	0.00004	0.00003
Al	%Max	<0.00001	<0.00001	0.00002	<0.00001	<0.00001	<0.00001	<0.00001	<0.00001	<0.00001	<0.00001
As	%Max	0.00027	0.00027	0.00046	0.00024	0.00014	0.00023	0.00019	0.00007	<0.00005	0.00016
Ca	%Max	0.00041	0.00035	0.00070	0.00042	0.00014	0.00038	0.00041	0.0013	0.0011	0.00029
Cu	%Max	0.0019	0.0011	0.0015	0.00059	0.00062	0.00035	0.0019	0.0025	0.0022	0.0017
Ni	%Max	0.00077	0.00007	0.00014	<0.00005	<0.00005	<0.00005	<0.00005	0.00058	0.00028	0.00027
Te	%Max	0.00026	0.00022	0.00044	0.00023	0.00010	0.00022	0.00028	0.00058	0.00039	0.00012
Zn	%Max	0.00027	0.00024	0.00027	0.00021	0.00018	0.00021	0.00015	0.00037	0.00030	0.00016

For the evaluation of result, the methods precision statement applies. The derived test results are only applicable to the sample(s) as received and identified as above. The report shall not be reproduced except in full without the written approval.



Kelorex Energy

SOFT LEAD 2

Elements	Amount	1123	1124	1125	1126	1127	1128	1129	1130	1131	1132
Pb	%Min	99.9875	99.9848	99.9857	99.9821	99.9805	99.9762	99.9738	99.9802	99.9773	99.9780
Sn	%Max	<0.00005	0.00020	<0.00005	0.00018	0.00013	0.00077	0.00093	0.00074	0.00088	0.00040
Ag	%Max	0.0017	0.0018	0.0019	0.0019	0.0019	0.0024	0.0021	0.0015	0.0018	0.0024
Sb	%Max	0.00038	0.00015	<0.00005	0.00039	0.00022	0.00048	0.00049	0.00057	0.00057	0.00039
Bi	%Max	0.0076	0.0107	0.0106	0.0138	0.0145	0.0165	0.0181	0.0131	0.0154	0.0158
Cd	%Max	0.00003	0.00004	0.00003	0.00004	0.00003	0.00005	0.00006	0.00005	0.00006	0.00004
Al	%Max	0.00005	0.00001	0.00002	0.00001	<0.00001	0.00003	0.00005	0.00003	0.00005	<0.00001
As	%Max	0.00033	0.00011	0.00016	0.00007	<0.00005	0.00067	0.00078	0.00070	0.00067	<0.00005
Ca	%Max	0.00063	0.000020	<0.00005	0.00017	0.00068	0.00069	0.00083	0.00065	0.00078	0.0011
Cu	%Max	0.0011	0.0011	0.00098	0.00073	0.0016	0.00073	0.0011	0.0010	0.00082	0.0011
Ni	%Max	0.00013	0.00016	0.00006	0.00012	0.00007	0.00031	0.00041	0.00032	0.00035	<0.00005
Te	%Max	0.00029	0.00041	0.00007	0.00038	0.00014	0.00078	0.00093	0.00082	0.00086	0.00037
Zn	%Max	0.00019	0.00022	0.00032	0.00022	0.00021	0.00039	0.00046	0.00032	0.00043	0.00029

For the evaluation of result, the methods precision statement applies. The derived test results are only applicable to the sample(s) as received and identified as above. The report shall not be reproduced except in full without the written approval.



Kelorex Energy

99.99% LEAD

Elements	Amount	1117	1122
Pb	%Min	99.9918	99.9904
Sn	%Max	<0.00005	<0.00005
Ag	%Max	0.0015	0.0014
Sb	%Max	0.00023	0.00029
Bi	%Max	0.0048	0.0064
Cd	%Max	0.00003	0.00003
Al	%Max	<0.00001	<0.00001
As	%Max	0.00018	0.00012
Ca	%Max	0.00025	0.00022
Cu	%Max	0.00037	0.00077
Ni	%Max	0.00008	<0.00005
Te	%Max	0.00061	0.00010
Zn	%Max	0.00015	0.00016

For the evaluation of result, the methods precision statement applies. The derived test results are only applicable to the sample(s) as received and identified as above. The report shall not be reproduced except in full without the written approval.